

Declaration of Conformity

In Accordance with ANSI/ISEA 125-2014 and ANSI/ASSP Z359.7-2019



Alexander Andrew, Inc. 1306 S. Alameda St Compton, CA 90221 (800) 719-4619

Declaration #

T1124038

Declaration Date

11/24/2021

Tested Item #

5042AF

Suspension Trauma Relief System, Zipper Closure, Arc Flash

Additional Items Conforming Under this Declaration:

Alexander Andrew, Inc. declares that the product(s) listed above is in conformity with the requirements of the following product standard(s):

FallTech Internal Test Requirements &
ASTM F887-20

Conformity Assessment Method in accordance with ANSI/ISEA 125-2014

Level 1

Level 2

Level 3

Level 1: FallTech Lab
Outside the Scope of
ISO/IEC Standard 17025:2005

Level 2: FallTech Lab
Within the Scope of
ISO/IEC Standard 17025:2005

Level 3: Independent 3rd Party Lab
accredited to
ISO/IEC Standard 17025:2005

Supporting
Documentation

PC-2438

Authorized Signature

Name

Zachary Winters

Title

Engineering Manager

Date

11/24/2021



International Accreditation Service, Inc
3060 Saturn St, Ste 100
Brea, CA 92821 +1 562-364-8201

FallTech Lab - TL-594
ISO/IEC 17025:2017
Alexander Andrew Inc dba FallTech

FallTech Test Report

| | | | | | | | |
|----------------------------|--|------------------------------|-------------------------------------|-----------------|--|-----------------|--|
| Test Report No. | PC-2438 | Rpt. Date | 11/24/2021 | Rpt. Rev | | Rev Date | |
| Report Prepared For | FallTech | | | | | | |
| Initiated By | Dan Redden | Test Specification(s) | FallTech Internal Test Requirements | | | | |
| Part No. | 5042AF | Part No. Revision | A | | | | |
| Part Description | Suspension Trauma Relief System, Zipper Closure, Arc Flash | | | | | | |
| Test Request No. | PC-2438 | Date Complete | 11/24/2021 | | | | |
| Test Operator(s) | Dan Redden | | | | | | |

Material/Sample Identification

| Sample ID | Description |
|-----------|--|
| S#1 | Suspension Trauma Relief System, Zipper Closure, Arc Flash (Non Arc'd) |
| S#2 | Suspension Trauma Relief System, Zipper Closure, Arc Flash (Arc'd) |

Test Summary

| Test Specification | Test Criteria | Test Result | Pass/Fail | |
|--------------------|-----------------|-------------|-----------|------|
| N/A | Static Strength | ≥ 500 Lbf | 523.9 Lbf | Pass |
| | Hold | ≥ 1 Minute | 1 Minute | Pass |
| N/A | Static Strength | ≥ 500 Lbf | 519.0 Lbf | Pass |
| | Hold | ≥ 1 Minute | 1 Minute | Pass |

Conclusion

| |
|--|
| Based upon the samples provided to the Lab: FallTech PN 5042AF Rev A meets the requirements of FallTech Internal Test Requirements and ASTM F887-20 |
|--|

Report Signatories and Approval

| | | | |
|-----------------------|-------------------|------|------------|
| Lab Technical Manager | <i>Dan Redden</i> | Date | 11/24/2021 |
|-----------------------|-------------------|------|------------|

End of Report





TESTING - EXPOSURE TO AN ELECTRIC ARC

Test Specimen:

Suspension Trauma Pack, Style RP05ALX (Sample A)
Webbing: Nylon, Black, Nomex Rip-stop Cover

Requested by:

FallTech
1306 S Alameda St
Compton, CA 90221

Test Standard:

ELECTRIC ARC TESTS: ASTM F887-20

OBSERVATION OF PERSONAL CLIMBING EQUIPMENT EXPOSED TO AN ELECTRIC ARC

Test Report:

K-580568-2109H01-R00

| | | |
|---------------------------------------|---------------------------------|---------------------------------|
| Sample Received September 15, 2021 | Test Date September 23, 2021 | Report Date October 27, 2021 |
|---------------------------------------|---------------------------------|---------------------------------|

Prepared by

Approved by

Robert Ferraz
Technologist, HCL
TD Technologies, Kinectrics

Claude Maurice
Technical Specialist, HCL
TD Technologies, Kinectrics

For questions about this test report, please contact testing@arcwear.com



Revision History

| | | | |
|-----|-------------------------|---------------|----------------|
| Rev | Description | | |
| 00 | Initial report creation | | |
| | Issue Date | Prepared by | Approved by |
| | October 27, 2021 | Robert Ferraz | Claude Maurice |
| Rev | Description | | |
| | Issue Date | Prepared by | Verified by |
| | | | |

DISCLAIMER

Kinectrics prepared this report as a work of authorship sponsored by their Client. This report has been prepared solely for the benefit of the Client and may not be used or relied upon in whole or in part by any other person or entity without Client permission or without Kinectrics' permission if required by the Contract between Client and Kinectrics Inc. Neither Kinectrics, their client nor any person acting on behalf of them: (a) makes any warranty or representation whatsoever, express or implied, or assumes any legal liability of responsibility for any third party's use, or the results of such use, with respect to (i) the use of any information, apparatus, method, process, or similar item disclosed in this report including the merchantability or fitness for any particular purpose of any information contained in this report or the respective works or services supplied or performed or (ii) that such use does not infringe on or interfere with privately owned rights, including any party's intellectual property; or (b) assumes responsibility for any damages or other liability whatsoever (including any consequential damages resulting from a third party's selection or use of this report or any information, apparatus, method, process, or similar item disclosed).

Copyright © 2021 Kinectrics Inc. All rights reserved.

QUALITY MANAGEMENT

The arc testing performed to the above mentioned Standard is accredited by the Standards Council of Canada (SCC) to conform to the requirements of CAN-P-4E (ISO/IEC 17025:2005). Accreditation by the Standards Council of Canada (SCC) is a mark of competence and reliability

- The test performed does not apply to electrical contact or electrical shock hazard.
- The test result is applicable only to the Test Specimens delivered to Kinectrics, other material, design or color may have a different response.
- It is the clients' responsibility to provide full and accurate information about the items supplied.
- No test is done to validate the fiber content or composition of the test item.
- Photographs of the test specimens and waveforms of the arc current, voltage and calorimeters with the circuit and arc exposure calibration records are available from Kinectrics and provided to the client separately from this report.



1 Test Standard:

Electrical arc test according to ASTM F887-20, Section 22

Standard Specifications for Personal Climbing Equipment, After Exposure to an Electric Arc Evaluation. Specimens are mounted on mannequins of panels having a distance of 30.5 cm (12 inches) from the centerline of the electrodes. The test standard requires that the finished personal climbing equipment be exposed to a level of 40 cal/cm² ± 5 cal/cm².

1.1 Test Requirements

Harnesses- The test program requires the specimens be placed on mannequins as normally worn. A minimum of eight samples are tested, four samples with the front facing the arc and four samples with the back side toward the arc.

Harness accessories, loops etc. - Three specimens of each accessory or loop are required to be exposed to the arc.

Energy Absorbing Lanyard - Three specimens of each lanyard are required to be exposed to the arc.

Other effects than the thermal effects of an electric arc like noise, light emissions, pressure rise, hot oil, electric shock, the consequences of physical and mental shock or toxic influences are not covered by this standard.

1.2 Acceptance criteria for products exposed to electrical arc:

The procedure outlined in ASTM F887-20 is followed to verify the electric arc performance of the personal climbing equipment. The product is considered as having passed the visual inspection criteria if the parameters defined in Table 1-1 are met. As proof of performance following the arc exposure, the exposed test specimens shall be subjected to a drop test. This shall be done as soon as practically possible. The samples have been returned to the client as directed to perform the drop test.

Table 1-1: Visual inspection Criteria for Electric Arc Performance of ASTM F887-20

| Parameter | Criterion |
|------------------|--|
| Arc Energy | Electrical arc exposure of 40 cal/cm ² ± 5 cal/cm ² |
| Ignition | No electric arc ignition. |
| After-flame Time | Less than 5 seconds on load bearing materials and less than 15 seconds for accessories or non-load bearing components. |
| Melting/Dripping | No melting and dripping of molten materials to the floor of any load bearing material. Accessories are allowed to exhibit melting and dripping provided they are not ignited while dripping. |

2 Test Condition:

The following test circuit parameters and conditions were used.

- Electric arc current: 8 kA rms \pm 10%, 60 Hz
- Open circuit voltage: 2500 V rms \pm 10%, 60 Hz
- Nominal Heat Flux Density: 2100 kW/m² (50 cal/cm²·s)
- Arc duration: 0.85 seconds \pm 0.1 s to obtain required incident energy
- Electrode gap: 305 mm (12 inches)
- Distance from mannequin to electrode: 305 mm (12 inches)
- Deviations and abnormalities: None

Note: The measurement uncertainty, MU, for the measured values of this test method are well within the requirements of the test standard and are defined on a 95% confidence interval basis over the full test range, as follows:

- Temperature: \pm 2 °C
- Arc Current: \pm 2.5%
- Time zero reference: \pm 3 ms
- Incident Energy: \pm 1.5%
- Voltage: \pm 2.2%

3 Test Specimen:

The following description of the test sample was provided by the client and confirmed by the sample shown in Figure 3.1.

| | |
|----------------------------------|---|
| Sample description: | FallTech, Suspension Trauma Pack |
| Sample identification: | Style RP05ALX (Sample A) |
| Manufacturer: | FallTech |
| Material: | Nylon Webbing, Nomex Ripstop Cover, Black |
| Number of samples tested: | 3 |
| Notes: | No Identification Tag |



Figure 3.1: Sample as Received



4 Test Results:

Arc exposures were performed on six samples as indicated. If the conditions and evaluation of the samples meet the criteria in Table 1-1, the product has passed the electrical arc exposure and is candidate for the mechanical drop test to fully meet the arc performance requirements of ASTM F887-20. Photographs of the samples before and after the arc exposure are shown in Section 6.

Table 4-1: Summary of Test Results

| Trial # 21-4649 | | |
|------------------------|--|----------------|
| Mannequin | A – 3 Samples Left, Center, Right | B – N/A |
| Position | Back, Back, Front | N/A |
| Item Serial # | N/A | N/A |
| Incident Energy | 40 Cal/cm ² | N/A |
| After-flame | 0 | N/A |
| Ignition | N | N/A |
| Melting and Dripping | N | N/A |
| Acceptance Criteria | Meets | N/A |

4.1 Observations:

Heavy charring was observed on all samples tested. There was no evidence of afterflame, melting or dripping on any of the samples tested.

5 Interpretation of Results:

This testing does not assign an arc rating to this product. The purpose of this test was to observe the response characteristics of this product when exposed to an open-air electric arc

Based on the test results in Table 4-1 and observations, the product tested meets the requirements criteria of Table 1-1 as per ASTM F887-20 sections 22.1-22.4 and 22.6.1-22.6.2.

The samples provided were tested as harness accessories since they are not part of a finished product. Verification of the final harness product is required for verification of performance and includes a mechanical integrity (vertical drop test) following the arc exposure.