

GUARDIAN® ANSI/ASSP Z359.13-2013

Pure Safety Group, Inc.
607 East Sam Houston Pkwy S
Suite 800, Pasadena, TX 77053

Test Report Number: 2025090811203
Job Number: Test 268
Product SKU#: 11203
Product Type: Energy Absorbing Lanyard
Product Description: 6ft Double Leg Internal Shock Lanyard with HS Snap/HS Rebar Hooks
Testing Standard: ANSI/ASSP Z359.13-2013 (R2022) Personal Energy Absorbers and Energy Absorbing Lanyards
Dates of Manufacture: 5/01/2024
Date(s) of Testing: 5/31/2024, 6/04/2024, 6/14/2024

REQUIREMENT VERIFICATION

<u>Requirement Description</u>	<u>Clause/Section</u>	<u>Result</u>
General Requirements	3. Requirements	Meets or Exceeds
Markings and Instructions	5. Marking and Referencing Literature	Meets or Exceeds

QUALIFICATION TESTING

<u>Test Description</u>	<u>Test Date</u>	<u>Clause/Section</u>	<u>Result</u>
Activation Force (PEA)	5/31/2024	4.2 Activation Force Testing of Personal Energy Absorbers	Pass
Static Strength (Y-Lanyards, Leg A)	6/04/2024	4.7.1 Static Strength Testing of Y-Lanyards	Pass
Static Strength (Y-Lanyards, Leg B)	6/04/2024	4.7.2 Static Strength Testing of Y-Lanyards	Pass
Static Strength (Y-Lanyards, Leg to Leg)	6/14/2024	4.7.3 Static Strength Testing of Y-Lanyards	Pass
Dynamic Performance (Y-Lanyards, Single Connection)	6/04/2024	4.8 Dynamic Performance Testing of Y-Lanyards - Single Connection	Pass
Dynamic Performance (Wet)	6/04/2024	4.13.1 Dynamic Performance Testing of Energy Absorbing Lanyards - Wet	Pass
Dynamic Performance (Cold)	6/04/2024	4.13.2 Dynamic Performance Testing of Energy Absorbing Lanyards - Cold	Pass
Dynamic Performance (Hot)	6/04/2024	4.13.3 Dynamic Performance Testing of Energy Absorbing Lanyards - Hot	Pass
Dynamic Performance (Y-Lanyards, Dual Connection)	6/04/2024	4.9 Dynamic Performance Testing of Y-Lanyards - Dual Connection	Pass
Dynamic Performance (Y-Lanyards, Hip Test)	6/04/2024	4.10 Dynamic Performance Testing of Y-Lanyards - Hip Test	Pass

This test report covers these additional products:

11113, 11200, 11201, 11202, 11222, 21215

Please contact quality@guardianfall.com for signed report.

TEST EQUIPMENT		
EQUIPMENT	MODEL	SERIAL
Load Cell	1220ACK-25K-B	347989A
Load Cell	1210ACK-10K-B	229097A
Tape Measure	TX1-25	20243698
Test Weight	282 lb	GFP001
Environmental Chamber	S-8-8200	46336
Environmental Chamber	SM-16-8200	49357
Scale	TLI	02314063019

Notes

--

3 Requirements		
3.1	Personal Energy Absorber Component. All Personal energy absorbers bearing this standard number shall meet the design and testing requirements of this standard.	Meets or Exceeds
3.1.1	Classifications. Personal energy absorbers shall be categorized as follows:	
3.1.1.1	"6ft FF" personal energy absorbers shall be designed for up to 6 foot (1.83m) free fall (FF indicates free fall) applications and users weighing between 130 and 310 pounds (59-140kg)	Meets or Exceeds
3.1.1.2	"12ft FF" personal energy absorbers shall be designed for up to 12 foot (3.66m) free fall applications (FF indicates free fall) and users weighing between 130 and 310 pounds. (59-140kg)	NA
3.1.2	Material. Material used in the construction of personal energy absorbers shall be made of virgin synthetic material having strength, aging, abrasion resistance and heat resistance characteristics equi+valent or superior to polyamides.	Meets or Exceeds
3.1.3	Terminations. Personal energy absorbers shall have end terminations which meet the following requirements:	
3.1.3.1	Spliced. Formed eye termination in rope shall be made in accordance with the rope manufacturer's recommendaton, subject to the following requirements. Eye splices in twisted rope having three or more strands shall have a minimum of four tucks. A properly sized thimble shall be part of a formed eye termination. Knots shall not be used to form energy absorbing lanyard end terminations. Terminations (including cut ends) and splices shall be seized, whipped or otherwise integrally finished to prevent the termination or splice from unraveling or unsplicing.	NA
3.1.3.2	Stitched. Stitched eye terminations on strap energy absorbers shall be sewn using lock stitches. Thread shall be of the same material type as the webbing and shall be of a contrasting color to facilitate inspection. Webbing shall be protected from concentrated wear at all interfaces with load bearing connector elements. Webbing ends shall be seared or otherwise prevented from unraveling.	Meets or Exceeds
3.1.3.3	Wire Rope. Formed eye terminations of wire rope shall have a minimum breaking strength of 80% of the wire rope when tested in accordance with ASTM E8/8M-11, Standard Test Methods of Tension Testing of Metallic Materials. The following methods may be used for forming eyes in wire rope: (a) spliced eye with one swaged fitting, or (b) return eye with a minimum of two swaged fittings. All formed eyes shall incorporate a properly sized thimble.	NA
3.1.3.4	Terminations other than splicing, stitching and swaging are permitted when it can be demonstrated by testing that the requirements of this standard can be met and additionally, that the durability, reliability, strength and other properties pertinent to the intended uses have been evaluated and determined suitable by the manufacturer.	Meets or Exceeds
3.1.4	Connectors. Personal energy absorbers shall have integrally attached connectors or be integral to the energy absorbing lanyard. Connectors used on all personal energy absorbers shall meet the requirements of ANSI/ASSE Z359.12, Safety Requirements for Connecting Components for Personal Fall Arrest Systems (PFAS) Connectors.	Meets or Exceeds
3.1.5	Deployment Indicator. Personal energy absorbers shall be designed such that it is obvious if they have been activated or by a warning flag or label that indicates activation.	Meets or Exceeds
3.1.6	Activation Force. Personal energy absorbers when subjected to a static force no less than 450lb (2kN) in accordance with 4.2 shall not show signs of activation or exhibit permanent elongation greater than 2in. (51mm)	Meets or Exceeds
3.1.7	Static Strength. Personal energy absorbers when statistically tested in accordance with 4.3 shall have a minimum breaking strength no less than 5,000lb (22kN)	NA
3.1.8	Personal Energy Absorber Dynamic Performance -Ambient Dry Test. Personal energy absorbers tested in accordance with 4.4 shall meet the following requirements:	NA
3.1.8.1	6ft FF personal energy absorbers shall have an average arrest force no greater than 900lb (4kN) and a maximum deployment distance of 48in. (1.2m) without exceeding 1,800lb (8kN) maximum arrest force.	Meets or Exceeds
3.1.8.2	12ft FF personal energy absorbers shall have an average arrest force no greater than 1,350lb (6kN) and a maximum deployment distance of 60in. without exceeding 1,800lb (8kN) maximum arrest force.	NA

3.1.9	Personal Energy Absorber Dynamic Performance - Conditioning Tests. Personal energy absorbers shall be conditioned according to the requirements of 4.13.1, 4.13.2 and 4.13.3 and tested according to 4.4. Conditioning tests do not need to be performed when the energy absorber is integral to a lanyard and the energy absorbing lanyard is tested according to 3.2.5.	Meets or Exceeds
3.1.9.1	Conditioned 6ft FF samples shall have an average arrest force no greater than 1,125lb (5kN) without exceeding 1,800lb (8kN) maximum arrest force and a maximum deployment distance of 60in. (1.5m)	Meets or Exceeds
3.1.9.2	Conditioned 12ft FF samples shall have an average arrest force no greater than 1,575lb (7kN) without exceeding 1,800lb (8kN) maximum arrest force and a maximum deployment distance of 60in. (1.5m).	NA
3.2	Energy Absorbing Lanyard Component. All energy absorbing lanyards bearing this standard number shall be equipped with a personal energy absorber or have energy absorbing ability that meet the design and testing requirements of this standard.	Meets or Exceeds
3.2.1	Material. Rope, webbing and tubular webbing used in the construction of energy absorbing lanyards shall be made of virgin synthetic material having strength, aging, abrasion resistance and heat resistance characteristics equivalent or superior to polyamides.	Meets or Exceeds
3.2.2	Terminations. Energy absorbing lanyards shall have end terminations which meet the following requirements.	
3.2.2.1	Spliced. Formed eye terminations in rope shall be made in accordance with the rope manufacturer's recommendation, subject to the following requirements. Eye splices in twisted rope having three or more strands shall have a minimum of four tucks. A properly sized thimble shall be part of a formed eye termination. Knots shall not be used to form energy absorbing lanyard end terminations. Terminations (including cut ends) and splices shall be seized, whipped, or otherwise integrally finished to prevent the termination or splice from unraveling or unsplicing.	NA
3.2.2.2	Stitched. Stitched eye terminations on strap energy absorbing lanyards shall be sewn using lock stitches. Thread shall be of the same material type as the webbing and shall be of a contrasting color to facilitate inspection. Webbing shall be protected from concentrated wear at all interfaces with load bearing connector elements. Webbing ends shall be seared or otherwise prevented from unraveling.	Meets or Exceeds
3.2.2.3	Wire Rope. Formed eye terminations of wire rope shall have a minimum breaking strength of 80% of the wire rope when tested in accordance with E8/8M-11, Test Methods of Tension testing of Metallic Materials. The following methods may be used for forming eyes in wire rope: (a) spliced eye with one swaged fitting, or (b) return eye with a minimum of two swaged fittings. All formed eyes shall incorporate a properly sized thimble.	NA
3.2.2.4	Terminations other than splicing, stitching, and swaging are permitted when it can be demonstrated by testing that the requirements of this standard can be met and additionally, that the durability, reliability, strength and other properties pertinent to the intended uses have been evaluated and determined suitable by the manufacturer.	Meets or Exceeds
3.2.3	Energy Absorbing Lanyard Connectors. Energy absorbing lanyards shall have integrally attached connectors. Connectors used on all personal energy absorbers shall meet the requirements of ANSI/ASSE Z359.12, Safety Requirements for Connecting Components for Personal Fall Arrest Systems (PFAS) Connectors.	Meets or Exceeds
3.2.4	Energy Absorbing Lanyard Dynamic Performance - Ambient Dry Test. Energy absorbing lanyards shall be tested as a complete system according to 4.5. The results of the tests shall meet the requirements of 3.2.4.1 and 3.2.4.2 respectively.	NA
3.2.4.1	6ft FF energy absorbing lanyards shall have an average arrest force no greater than 900lb (4kN) and a maximum deployment distance of 48in. (1.2m) without exceeding 1,800lb (8kN) maximum arrest force.	Meets or Exceeds
3.2.4.2	12ft FF energy absorbing lanyards shall have an average arrest force no greater than 1,350lb (6kN) and a maximum deployment distance of 60in. (1.5m) without exceeding 1,800lb (8kN) maximum arrest force.	NA

Notes

3.2.5	Energy Absorbing Lanyards Dynamic Performance - Conditioning Tests. Energy absorbing lanyards shall be conditioned according to the requirements of 4.13.1, 4.13.2 and 4.13.3 and tested according to 4.5	Meets or Exceeds
3.2.5.1	Conditioned 6ft FF samples shall have an average arrest force no greater than 1,125lb (5kN) without exceeding 1,800lb (8kN) maximum arrest force and a maximum deployment distance of 48in. (1.2m)	Meets or Exceeds
3.2.5.2	Conditioned 12ft FF samples have an average arrest force no greater than 1,575lb (7kN) without exceeding 1,800lb (8kN) maximum arrest force and a maximum deployment distance of 60in. (1.5m).	NA
3.2.6	Static Strength. Energy absorbing lanyards when statically tested in accordance with 4.6 shall have a minimum breaking strength no less than 5,000lb (22.2kN). Energy absorbing lanyards that incorporate a means for length (disregarding elastic stretch) up to a load of 2,000lb (8.8kN).	Meets or Exceeds
3.2.7	Abrasion Test. Wrap-around energy absorbing lanyards shall be additionally tested in accordance with 4.12. The wrap-around energy absorbing lanyard shall have a minimum breaking strength no less than 3,600lb (16kN) after being abraded.	NA
3.2.8	Static Test - Wrap-Around Energy Absorbing Lanyards. Energy absorbing lanyards that are designed to wrap-around a structure and connect back to themselves shall be tested in accordance with 4.11. The energy absorbing lanyard shall have a minimum breaking strength no less than 5,000lb (22.2kN) when connected as designed and instructed for use.	NA
3.2.9	Static Test - Y-Lanyards. Y-lanyards shall be statically tested in accordance with 4.7 and shall have a minimum breaking strength no less than 5,000lb (22.2kN)	Meets or Exceeds
3.2.10	Dynamic Performance Testing of Y-Lanyards. Y-lanyards shall be tested in accordance with 4.8, 4.9 and 4.10 and shall meet the following requirements:	Meets or Exceeds
3.2.10.1	Y-Lanyards Single Connection. 6ft FF and 12ft FF Y-lanyards shall be tested in accordance with 4.8 and meet the respective requirements of 3.1.8.1 and 3.1.8.2.	Meets or Exceeds
3.2.10.2	Y-Lanyards Dual Connection. 6ft FF and 12ft FF Y-lanyards shall be tested in accordance with 4.9 and shall not at any time exceed a force reading over 1,800lb (8kN).	Meets or Exceeds
3.2.10.3	Dynamic Test - Hip Connection. Y-Lanyards shall be tested in accordance with 4.10. If the energy absorbing lanyard breaks the nylon keeper during the test, the energy absorbing lanyard shall include a warning label on each lanyard leg according to 5.2.2.	Meets or Exceeds

Notes

5.1 General Marking Requirements		
5.1.1	Markings shall be in English	
5.1.2	The legibility and attachment of required markings shall endure for the life of the component, subsystem or system being marked. When pressure sensitive labels are used, they shall comply with the applicable provision of UL 969-89, Marking and Labeling Systems	Meets or Exceeds
5.1.3	Equipment shall be marked with the following: -Part number and model designation; -Year of manufacture; -Manufacturer's name or logo; -Capacity rating; -Serial number; -Standard number; -Warning to follow the manufacturer's instructions included with the equipment at time of shipment from the manufacturer.	Meets or Exceeds
5.2 Specific Marking Requirements		
5.2.1	Personal Energy Absorbers and Energy Absorbing Lanyards. Personal energy absorbers and energy absorbing lanyards shall be marked to identify: -The fiber used in the material of construction; -The length; -The need to avoid contact with sharp edges and abrasive surfaces; -The need to make only compatible connections; -The maximum elongation; -Restriction, if any, on the types of components, subsystems or systems with which the personal energy absorber is designed to be used; -The average arrest force, maximum free fall distance and capacity of the personal energy absorber in a separate label identical in size, color, and content; -6ft FF personal energy absorbers shall be in black print on a contrasting white background; -12ft FF personal energy absorbers shall be in white print on a contrasting black background.	Meets or Exceeds
5.2.2	Y-Lanyard. In addition to 5.2.1, Y-lanyards that fail the Dynamic Hip Test detailed in 3.2.10, must include a warning label on both connecting ends of the lanyard specifically directing users how to safely store the unused leg of the lanyard.	Meets or Exceeds
5.3 General Instruction Requirements		
5.3.1	Instructions shall be provided to the user, printed in English, and affixed to the equipment at the time of shipment from the manufacturer.	Meets or Exceeds
5.3.2	Instructions shall contain the following information: -A statement that the manufacturer's instructions shall be provided to the users; -Manufacturer's name, address and telephone number; -Manufacturer's part number and model designation for the equipment; -Intended use and purpose of the equipment; -Proper method of use and limitations on use of the equipment; -Illustrations showing locations of markings on the equipment; -Reproduction of printed information on all markings; -Inspection procedures required to assure the equipment is in serviceable condition and operating correctly; -Anchorage requirements; -An illustration of how to calculate free fall distances; -Criteria for discarding equipment which fails inspection; -Procedures for cleaning, maintenance and storage; -Reference to the ANSI/ASSE Z359.13, Personal Energy Absorbers and Energy Absorbing Lanyards, standard and applicable regulations governing occupational safety.	Meets or Exceeds

5.3.3	Instructions shall require that only the equipment manufacturer, or persons or entities authorized in writing by the manufacturer, shall make repairs to the equipment.	Meets or Exceeds
5.3.4	Instructions shall require the user to remove equipment from field service if it has been subjected to the forces of arresting a fall.	Meets or Exceeds
5.4	Specific Instruction Requirements	
5.4.1	Personal Energy Absorbers. In addition to general instruction requirements, written instructions for personal energy absorbers shall include: -The material used in personal energy absorber construction; -The need to make only compatible connections and limitations of compatibility; -Proper method of coupling the personal energy absorber to adjacent components of the system; -The maximum arrest force of the personal energy absorber when dynamically tested in accordance with the requirements of this standard; -The maximum elongation of the personal energy absorber when dynamically tested in accordance with the requirements of this standard; -A reference chart that indicates the deployment distance of the personal energy absorber according to the user weight and free fall distance; -A statement that indicates information necessary in designing fall protection systems shall be made available from the manufacturer. Manufacturers may provide designers of fall protection systems a representative graph(s) of the time history plot of the loading from a drop test.	Meets or Exceeds

Notes

All measurements expressed at approximately 95% confidence level using coverage factor K=2
--

4.2 Activation Force Testing of Personal Energy Absorbers

Requirements per Section 3.1.6

- a) Measure and record the length of the personal energy absorber from bearing point to bearing point when it is under a tension of 10 $\pm$ 0.5/-0 pounds.
- b) Connect the Personal Energy Absorber test specimen between the connectors of the tensile test equipment specified in 4.1.6 by means of the connectors at each end of the personal energy absorber. If the test specimen is a component of a subsystem or system, and does not have an integral connector at its end, simulate as closely as possible the intended means of assembling it into its subsystem or system.
- c) Subject the personal energy absorber to a force no less than 450 lb (2 kN) for a period no less than 1 minute.
- d) Examine the personal energy absorber for signs of activation and record the results of this examination
- e) Remove the personal energy absorber from the tensile test equipment and allow the personal energy absorber to recover in an untensioned position for a period of one hour.
- f) Measure and record the length of the personal energy absorber when it is subjected to a tension of 10 $\pm$ 0.5/-0 lb.
- g) Calculate the permanent personal energy absorber elongation.
- h) Compare the test results set forth in the requirements of 3.1.6

4.2 Activation Force Testing of Personal Energy Absorbers

Requirements per Section 3.1.6

Samples	Sample # 28	Sample # 29	Sample # 30
Actual force applied (lb)	467.90	468.77	468.81
Length of specimen under 10lb tension (Pre-test) (in.)	70.25	70.75	70.875
Length of specimen under 10lb tension (Post-test) (in.)	71.375	71.75	71.875
Permanent elongation (>2") (in.)	1.125	1.0	1.0
Result/Assessment	Pass	Pass	Pass

Notes

4.7.1 Static Strength Testing of Y-Lanyards, Leg A Requirements per Section 3.2.9

- Connect the energy absorbing lanyard test specimen between the connectors of the tensile test equipment specified in 4.1.
- Attach the central connector intended to connect to the harness and one connector on one of the energy absorbing lanyard legs into the connectors of the tensile test equipment
- Subject the energy absorbing lanyard to a force no less than 5,000 pounds (22.2kN) for a period no less than 1 minute. The time to reach this force shall be no less than 3 minutes to avoid dynamic effects.
- Compare the test results set forth in the requirements of 3.2.9

4.7.1 Static Strength Testing of Y-Lanyards, Leg A Requirements per Section 3.2.9

Samples	Sample # 01	Sample # 02	Sample # 03
Actual Load applied (>5,000lb) (lb)	5012.36	5015.33	5013.60
Specimen maintained load	Yes	Yes	Yes
Result/Assessment	Pass	Pass	Pass

4.7.2 Static Strength Testing of Y-Lanyards, Leg B Requirements per Section 3.2.9

- Connect the energy absorbing lanyard test specimen between the connectors of the tensile test equipment specified in 4.1.
- Conduct the same test in 4.7.1 using the alternate energy absorbing lanyard leg
- Subject the energy absorbing lanyard to a force no less than 5,000 pounds (22.2kN) for a period no less than 1 minute. The time to reach this force shall be no less than 3 minutes to avoid dynamic effects.
- Compare the test results set forth in the requirements of 3.2.9

4.7.2 Static Strength Testing of Y-Lanyards, Leg B Requirements per Section 3.2.9

Samples	Sample # 04	Sample # 05	Sample # 06
Actual Load applied (>5,000lb) (lb)	5009.79	5008.22	5012.61
Specimen maintained load	Yes	Yes	Yes
Result/Assessment	Pass	Pass	Pass

4.7.3 Static strength Testing of Y-Lanyards, Leg to Leg Requirements per Section 3.2.9

- Connect the energy absorbing lanyard test specimen between the connectors of the tensile test equipment specified in 4.1.
- Conduct the same test between the two energy absorbing lanyard legs that are intended to connect to the anchorage
- Subject the energy absorbing lanyard to a force no less than 5,000 pounds (22.2kN) for a period no less than 1 minute. The time to reach this force shall be no less than 3 minutes to avoid dynamic effects.
- Compare the test results set forth in the requirements of 3.2.9

4.7.3 Static strength Testing of Y-Lanyards, Leg to Leg Requirements per Section 3.2.9

Samples	Sample # 07	Sample # 08	Sample # 09
Actual Load applied (>5,000lb) (lb)	5019.31	5025.57	5019.28
Specimen maintained load	Yes	Yes	Yes
Result/Assessment	Pass	Pass	Pass

Notes

4.8 Dynamic Performance Testing of Y-Lanyards - Single connection Requirements per Section 3.2.10.1

- a) Use the drop test structure, test weight, test instrumentation and quick release mechanism specified in 4.1.
- b) Measure and record the length of the energy absorbing lanyard from bearing point to bearing point when tensioned to 20, +0.5/-0 pounds, (9, +0.2/-0 kg).
- c) Attach the anchoring end of the Y-lanyard leg to the load cell and the harness connection to the test weight.
- d) The unused leg of the Y-lanyard can be hung loosely not connected to the test weight or load cell.
- e) If the personal energy absorber is a component of a sub-system or system, and does not have an integral connector at its end, simulate as closely as possible the intended means of assembling it into its sub-system or system.
- f) Attach the quick release mechanism to the test weight and raise the weight to the applicable level described in 4.4.1 or 4.4.2.
- g) The test weight shall be released from a point no more than 12 inches (305 mm) horizontally from the point of connection to the load cell.
- h) Release the test weight using the quick release mechanism.
- i) As a minimum, record the entire event and collect data to calculate force average and maximum arrest force.
- j) Measure and record the length of the energy absorbing lanyard from bearing point to bearing point while the weight is still suspended.
- k) Calculate the personal energy absorber elongation.
- l) Compare the test results set forth in the requirements of 3.2.10.1.

4.8 Dynamic Performance Testing of Y-Lanyards - Single connection Requirements per Section 3.2.10.1

Samples	Sample # 13	Sample # 14	Sample # 15
Max Arrest Force (<1,800 lb) (lb)	955.17	943.05	969.45
Average Arrest Force (lb) (<900lb for 6') (1,350lb for 12')	785.08	784.30	795.28
Permanent elongation (<60") (in.) (<48" for 6') (<60" for 12')	37.0	36.0	37.25
Result/Assessment	Pass	Pass	Pass

Notes

4.8 Dynamic Performance Testing of Y-Lanyards - Single connection - Wet Requirements per Section 3.2.10.1, 4.13.1

- a) Use the drop test structure, test weight, test instrumentation and quick release mechanism specified in 4.1.
- b) Measure and record the length of the energy absorbing lanyard from bearing point to bearing point when tensioned to 20, +0.5/-0 pounds, (9, +0.2/-0 kg).
- c) Attach the anchoring end of the Y-lanyard leg to the load cell and the harness connection to the test weight.
- d) The unused leg of the Y-lanyard can be hung loosely not connected to the test weight or load cell.
- e) If the personal energy absorber is a component of a sub-system or system, and does not have an integral connector at its end, simulate as closely as possible the intended means of assembling it into its sub-system or system.
- f) Attach the quick release mechanism to the test weight and raise the weight to the applicable level described in 4.4.1 or 4.4.2.
- g) The test weight shall be released from a point no more than 12 inches (305 mm) horizontally from the point of connection to the load cell.
- h) Release the test weight using the quick release mechanism.
- i) As a minimum, record the entire event and collect data to calculate force average and maximum arrest force.
- j) Measure and record the length of the energy absorbing lanyard from bearing point to bearing point while the weight is still suspended.
- k) Calculate the personal energy absorber elongation.
- l) Compare the test results set forth in the requirements of 3.2.10.1.

4.8 Dynamic Performance Testing of Y-Lanyards - Single connection - Wet Requirements per Section 3.2.10.1, 4.13.1

Samples	Sample # 16	Sample # 17	Sample # 18
Max Arrest Force (<1,800 lb) (lb)	1037.75	1057.49	1052.73
Average Arrest Force (lb) (<1,125lb for 6') (<1,800lb for 12')	819.0	831.41	832.16
Permanent elongation (<60") (in.) (<48" for 6') (<60" for 12')	35.0	35.5	35.25
Result/Assessment	Pass	Pass	Pass

Notes

4.8 Dynamic Performance Testing of Y-Lanyards - Single connection - Cold Requirements per Section 3.2.10.1, 4.13.2

- a) Use the drop test structure, test weight, test instrumentation and quick release mechanism specified in 4.1.
- b) Measure and record the length of the energy absorbing lanyard from bearing point to bearing point when tensioned to 20, +0.5/-0 pounds, (9, +0.2/-0 kg).
- c) Attach the anchoring end of the Y-lanyard leg to the load cell and the harness connection to the test weight.
- d) The unused leg of the Y-lanyard can be hung loosely not connected to the test weight or load cell.
- e) If the personal energy absorber is a component of a sub-system or system, and does not have an integral connector at its end, simulate as closely as possible the intended means of assembling it into its sub-system or system.
- f) Attach the quick release mechanism to the test weight and raise the weight to the applicable level described in 4.4.1 or 4.4.2.
- g) The test weight shall be released from a point no more than 12 inches (305 mm) horizontally from the point of connection to the load cell.
- h) Release the test weight using the quick release mechanism.
- i) As a minimum, record the entire event and collect data to calculate force average and maximum arrest force.
- j) Measure and record the length of the energy absorbing lanyard from bearing point to bearing point while the weight is still suspended.
- k) Calculate the personal energy absorber elongation.
- l) Compare the test results set forth in the requirements of 3.2.10.1.

4.8 Dynamic Performance Testing of Y-Lanyards - Single connection - Cold Requirements per Section 3.2.10.1, 4.13.2

Samples	Sample # 19	Sample # 20	Sample # 21
Max Arrest Force (<1,800 lb) (lb)	1020.47	1080.5	1095.79
Average Arrest Force (lb) (<1,125lb for 6') (<1,800lb for 12')	897.56	952.07	942.31
Permanent elongation (<60") (in.) (<48" for 6') (<60" for 12')	27.5	24.75	25.375
Result/Assessment	Pass	Pass	Pass

Notes

4.8 Dynamic Performance Testing of Y-Lanyards - Single connection - Hot Requirements per Section 3.2.10.1, 4.13.3

- a) Use the drop test structure, test weight, test instrumentation and quick release mechanism specified in 4.1.
- b) Measure and record the length of the energy absorbing lanyard from bearing point to bearing point when tensioned to 20, +0.5/-0 pounds, (9, +0.2/-0 kg).
- c) Attach the anchoring end of the Y-lanyard leg to the load cell and the harness connection to the test weight.
- d) The unused leg of the Y-lanyard can be hung loosely not connected to the test weight or load cell.
- e) If the personal energy absorber is a component of a sub-system or system, and does not have an integral connector at its end, simulate as closely as possible the intended means of assembling it into its sub-system or system.
- f) Attach the quick release mechanism to the test weight and raise the weight to the applicable level described in 4.4.1 or 4.4.2.
- g) The test weight shall be released from a point no more than 12 inches (305 mm) horizontally from the point of connection to the load cell.
- h) Release the test weight using the quick release mechanism.
- i) As a minimum, record the entire event and collect data to calculate force average and maximum arrest force.
- j) Measure and record the length of the energy absorbing lanyard from bearing point to bearing point while the weight is still suspended.
- k) Calculate the personal energy absorber elongation.
- l) Compare the test results set forth in the requirements of 3.2.10.1.

4.8 Dynamic Performance Testing of Y-Lanyards - Single connection - Hot Requirements per Section 3.2.10.1, 4.13.3

Samples	Sample # 22	Sample # 23	Sample # 24
Max Arrest Force (<1,800 lb) (lb)	930.79	898.38	931.57
Average Arrest Force (lb) (<1,125lb for 6') (<1,800lb for 12')	749.64	743.68	762.01
Permanent elongation (<60") (in.) (<48" for 6') (<60" for 12')	41	39.875	39.75
Result/Assessment	Pass	Pass	Pass

Notes

4.9 Dynamic Performance Testing of Y-Lanyard - Dual Connection *Requirements per Section 3.2.10.2*

- a) Use the drop test structure, test weight, test instrumentation and quick release mechanism specified in 4.1.
- b) Attach both ends of the energy absorbing lanyard to the load cell and the harness connector to the test weight.
- c) Attach the quick release mechanism to the applicable level described in 4.4.1 or 4.4.2.
- d) The test weight shall be released from a point no more than 12 inches (305 mm) horizontally from the point of connection to the load cell.
- e) Release the test weight using the quick release mechanism.
- f) Compare the test results set forth in the requirements of 3.2.10.2. See Figure 13a and 14a.

4.9 Dynamic Performance Testing of Y-Lanyard - Dual Connection *Requirements per Section 3.2.10.2*

Samples	Sample # 25	Sample # 26	Sample # 27
Drop Height (in.)	72	72	72
Maximum Arrest Force (<1,800lb) (lb)	1613.27	1632.47	1615.33
Result/Assessment	Pass	Pass	Pass

4.10 Dynamic Performance Testing of Y-Lanyards - Hip Test *Requirements per Section 3.2.10.3*

- a) Use the drop test structure, test weight, and quick release mechanism specified in 4.1.
- b) Attach one end of the energy absorbing lanyard to the test structure, the harness connector to the test weight and the unused leg to the connector on the side of the test weight (as illustrated in Figure 13b and 14b) using the nylon keeper specified in 4.1.11 with a 3 inch (76 mm) diameter loop.
- c) Attach the quick release mechanism to the applicable level described in 4.4.1 or 4.4.2.
- d) The test weight shall be released from a point no more than 12 inches (305 mm) horizontally from the point of connection to the load cell.
- e) Release the test weight using the quick release mechanism. Compare the test results set forth in the requirements of 3.2.10.3. See Figures 13b and 14b.

4.10 Dynamic Performance Testing of Y-Lanyards - Hip Test *Requirements per Section 3.2.10.3*

Samples	Sample # 10	Sample # 11	Sample # 12
Nylon keeper intact?	Yes	Yes	Yes
Result/Assessment	Pass	Pass	Pass

Notes

Pictured: 11200
Represents all part #s



Pictured: 11201
Represents all part #s



Pictured: 11202
Represents all part #s



Pictured: 21215
Represents all part #s



Labels
Applicable to all part #s



**Shock
Absorbing Lanyard**

ANSI Z359.13,
OSHA 1910.140,
OSHA 1926.502

Capacity (incl. tools):
130-310 lb (59-140 kg)

Maximum Deployment:
48 in (1,2 m)

Material:
Polyester, Nylon,
Galvanized Steel &
Aluminum.

**Attach shock absorber
end of lanyard to
dorsal D-ring on
full-body harness.**

Assembled in USA

**DO NOT REMOVE
LABELS**

90000 Rev. N-1

INSPECTED BY:

Date: Initials:

Date of First Use:

User must inspect before
each use. Competent
Person to inspect and
initial at least every 12
months.

Product lifetime is indef-
inite, as long as product
passes all inspection
requirements.

90000 Rev. N-2

⚠ WARNING!

Follow manufacturer's
instructions provided
with this lanyard at
time of shipment from
manufacturer. Fully read
and understand these
instructions before using.

Improper use of this
product could result in
serious injury or death.
Avoid contact with sharp
edges and abrasive
surfaces that can cut or
damage the webbing or
components.

Make only safe and
compatible connections.

For use only with other
OSHA and ANSI
compliant equipment
as part of a personal fall
arrest system.

Remove from service if
subjected to fall.

90000 Rev. N-3

WARNING!

**UNUSED LANYARD
LEG MUST ALWAYS
BE STORED AT
COMPATIBLE
HARNES LANYARD
KEEPER.**

90641 (Rev. B)